

February, 2015

3M™ Adhesive Transfer Tape with Plasticizer Resistant Adhesive F9465PC

Product Description

3M™ Adhesive Transfer Tape F9465PC is an acrylic pressure sensitive adhesive which has been formulated for bonding to many flexible vinyls and provide outstanding resistance to the effects of plasticizer migration from flexible vinyls.



3M™ Adhesive Transfer Tape with Plasticizer Resistant Adhesive F9465PC

General Information

Note: Vinyl formulations differ and plasticizer types and amounts can vary. The most common types of plasticized vinyl contain low molecular weight materials (plasticizers) which tend to migrate out of the vinyl. In the case of adhesive bonding, these plasticizers migrate into the adhesive which can cause softening of the adhesive and loss of bond strength over time.

- The possible effect of plasticizer migration on an adhesive bond can be predicted by accelerated aging for 5 days at elevated temperature (150°F [65°C]). Note: Due to the variability of vinyl formulations, we strongly recommend that the user test each vinyl substrate to determine suitability of the tape for the particular application.
- Natural and synthetic rubber materials such as neoprene and EPDM are also formulated with fillers and plasticizers. Note: 3M™ Adhesive Transfer Tape F-9465PC does not resist the effects of these particular fillers and plasticizers and is not recommended for use in bonding these materials.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values		Notes
Adhesive Thickness	0.13 mm	5 mil	The thickness listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc. While past data pages have listed nominal thicknesses, the coat weight (and theoretical caliper) has not changed.
Liner	Polycoated Paper		
Liner Thickness	0.1 mm	4.2 mil	The thickness listed is based on a calculation from manufacturing controlled adhesive coat weights using a density of 1.012 g/cc. While past data pages have listed nominal thicknesses, the coat weight (and theoretical caliper) has not changed.
Liner Color	Tan, printed		

Typical Performance Characteristics

Property	Values		Test Condition	Notes	Method	Substrate
Static Shear	10,000 min		500 g @ Room Temperature	1/2 in x 1 in sample size; Test terminated at 10,000 min		

Table continued on next page

Typical Performance Characteristics (continued)

Property	Values		Test Condition	Notes	Method	Substrate
180° Peel Adhesion	8.1 N/cm	74 oz/in	Room Temperature		ASTM D3330	Stainless Steel

Available Sizes

Property	Values		Notes
Master Width	1371.6 mm	54 in	More sizes may be available. Please call 800-223-7427 or talk to your local 3M representative for more information.

Environmental Performance

Bond Build-up: The bond strength of 3M™ Plasticizer Resistant Adhesive increases as a function of time and temperature

Temperature/Heat Resistance: 3M™ Plasticizer Resistant Adhesive is usable for short periods (minutes, hours) at temperatures up to 200°F (94°C) and for intermittent longer periods (days, weeks) up to 160°F (71°C).

Lower Temperature Service Limit: -40°F (-40°C).

UV Resistance: When properly applied, parts are not adversely affected by outdoor exposure.

Handling/Application Information**Application Ideas**

- Attaching flexible vinyl graphics to sporting helmets
- Attaching flexible vinyl films and graphics to signs
- Attaching flexible vinyl graphics to vehicles
- Attaching flexible vinyl graphics to collectibles
- Attaching flexible vinyl tubing

Storage and Shelf Life

Store in original cartons at 70°F (21°C) and 50% relative humidity.

When stored under proper conditions, product retains its performance and properties for 24 months from date of manufacture.

Trademarks

3M is a trademark of 3M Company.

References**Safety Data Sheet (SDS)**

https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=F9465PC

3M™ Adhesive Transfer Tape with Plasticizer Resistant Adhesive F9465PC

Family Group

	F9465PC	F9467U
Adhesive Thickness (mm)	0.13	0.089
Liner	Polycoated Paper	Polycoated Paper
Liner Thickness (mm)	0.1	0.1
Liner Color	Tan, printed	Tan

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

For Additional Information

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit www.3M.com/adhesives. Address correspondence to: 3M Industrial Adhesives and Tapes Division, Building 21-1W-10, 900 Bush Avenue, St. Paul, MN 55144-1000. Our fax number is 651-778-4244. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

Recognition/Certification

TSCA: This product is defined as an article under the Toxic Substances Control Act and therefore, it is exempt from inventory listing requirements MSDS: 3M has not prepared a MSDS for this product which is not subjected to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R.1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, this product should not present a health and safety hazard. However, use or processing of the product in a manner not in accordance with the directions for use may affect its performance and present potential health and safety hazards. Note: One of 3M's core values is to respect our social and physical environment. 3M is committed to comply with ever-changing, global, regulatory and consumer environmental, health, and safety (EHS) requirements. As a service to our customers, 3M is providing information on the regulatory status of many 3M products. Further regulation information including that for OSHA, USCPSI, FDA, California Proposition 65, READY and RoHS, can be found at 3M.com/regs.

Technical Information

The technical information and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed. It has been prepared from testing that was performed using standard test methods, and tested equipment that is calibrated in compliance to ISO9001 and operated by trained professionals in controlled environments. The data should be considered representative or typical only and should not be used for specification purposes. 3M reserves the right to make changes to the design, construction and technical data of products without prior warning.

Product Selection and Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluation the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence, or strict liability.

