

## Robust nitrile exam gloves, ensuring hand protection for diverse applications

- **Improved durability:** MICROFLEX® Supreno® SE SU-690 exam gloves are made with a strong nitrile formulation, offering wearers robust personal protection
- **Strong grip:** These gloves' textured fingertips ensure better grip when handling tools and equipment
- **Low AQL:** 0.65 AQL means these gloves offer excellent barrier protection against potentially hazardous substances



### Industries

- Automotive
- Automotive Aftermarket
- Life Sciences
- Healthcare
- Agriculture
- Emergency Medical Services
- Utilities
- Warehousing

### Recommended For

- Inspection, selecting, checking parts
- Assembly and inspection of components
- Picking and fastening components
- Equipment repair and maintenance
- General Purpose Auto Aftermarket
- Oil, fluids and filter change
- Engine transmission and repair
- Tire rotation & changes
- Maintaining lab furniture and equipment
- Assembly of parts
- Sample taking and processing
- Raw material sample collection
- Higher-risk clinical applications
- Protection from Type I latex allergy in HCW's or patients

TECHNICAL DATA SHEET

	Product Information
External Glove Surface	Textured Fingers
Audit Standards	EN ISO 13485:2012
Product Certification	ASTM D6319, EU Food Contact Approved, EN 1149-1/2/3, EN ISO 21420:2020, FDA21 CFR 177-2600-US Food Contact Approved, US QSR/FDA 510(k) Medical Examination Grade
Packaging Overview	100 gloves per dispenser 10 dispensers per case 1000 gloves per case
Storage Instructions	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.
Country Of Origin	Malaysia
Product Segmentation	Robust
Antistatic	Yes
Silicone Free	No

PHYSICAL PROPERTIES

	Typical Values		Testing Method
Length (mm/inches)	245 / 9.6		ASTM D3767,EN 420
Freedom from Holes (Inspection level I)	0.65 AQL		ASTM D5151,EN 455-1
Palm Thickness (mm/mils)	0.11 / 4.3		ASTM D3767,EN 420
Finger Thickness (mm/mils)	0.18 / 7.1		ASTM D3767,EN 420
	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength (MPa)	32	27	ASTM D412 & D573
Elongation at Break (%)	550	500	ASTM D412
Force at break (N)	12	9	EN 455-2

ORDERING INFORMATION

Size	XS (5.5 - 6)	S (6.5 - 7)	M (7.5 - 8)	L (8.5 - 9)	XL (9.5 - 10)	XXL (10.5 - 11)
Product Code	SU-690-XS	SU-690-S	SU-690-M	SU-690-L	SU-690-XL	SU-690-XXL

Performance Standards and Regulatory Compliance



For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at

<b>Europe, Middle East &amp; Africa Region</b> Ansell Healthcare Europe NV T: +32 (0) 2 528 74 00 F: +32 (0) 2 528 74 01  <b>Asia Pacific Region</b> MY: +603 8310 6688 apac.medical@ansell.com CN: +86 21 38275000 infochina@ansell.com JP: +813 5549 8151 info.medical.jp@ansell.com	<b>North America Region</b> Ansell Healthcare Products LLC T: +1 800 800 0444 F: +1 800 800 0445  <b>Latin America &amp; Caribbean Region</b> BR: +55 (11) 3356-3100 latam.medical@ansell.com MX: +52 442 296 2050 latam.medical@ansell.com CO: +57 1 288 3247 latam.medical@ansell.com	<b>Australia</b> Ansell Limited T: +61 1800 337 041 F: +61 1800 803 578  <b>Russia</b> Ansell PYC Ten. +7 495 258 13 16
---	--	--

Ansell, ® and ™ are trademarks owned by Ansell Limited or one of its affiliates. US Patented and US and non-US Patents Pending; [www.ansell.com/patentmarking](http://www.ansell.com/patentmarking) © 2025 Ansell Limited. All Rights Reserved.

Neither this document nor any other statement made herein by or on behalf of Ansell should be construed as a warranty of merchantability or that any Ansell product is fit for a particular purpose. Ansell assumes no responsibility for the suitability or adequacy of an end user's selection of gloves for a specific application.

