



Scotch® Paper Masking Tape 202

Product Data Sheet

Date: 06.2004

Supersedes: Date: 12.1995

Product Description	Scotch® Tape 202 is a chamois coloured smooth creped paper masking tape to perform well in most industrial painting situations.
Key Features	<ul style="list-style-type: none">* Latex saturated smooth creped paper backing* Controlled cross linked rubber resin adhesive
Advantages	<ul style="list-style-type: none">* Conformability* Solvent and water resistance* Sliver resistance* Easy hand tear* Good instant adhesion* Good holding power* Controlled unwind
Benefits	<ul style="list-style-type: none">* Good curve masking* Prevents paint bleed through* Easy removal* Good handling* Sticks easy* Resists lifting* Easy handling

Physical Properties	<table border="1"><tr><td>Thickness (AFERA 4006) Total</td><td>0.180 mm</td></tr></table>	Thickness (AFERA 4006) Total	0.180 mm
Thickness (AFERA 4006) Total	0.180 mm		

Performance Characteristics	<table border="1"><tr><td>Adhesion to Stainless Steel e.g. 90°/180° peel @room temp, 72 hr dwell, jaw speed 300mm/min AFERA 4001</td><td>9.5 N/25 mm</td></tr><tr><td>Temperature Performance</td><td>90 °C</td></tr><tr><td>Tensile Strength e.g. ASTM D-3759 / AFERA 4004</td><td>122 N/25 mm</td></tr><tr><td>Elongation at Break ASTM D-3759 / AFERA 4005</td><td>8 %</td></tr></table>	Adhesion to Stainless Steel e.g. 90°/180° peel @room temp, 72 hr dwell, jaw speed 300mm/min AFERA 4001	9.5 N/25 mm	Temperature Performance	90 °C	Tensile Strength e.g. ASTM D-3759 / AFERA 4004	122 N/25 mm	Elongation at Break ASTM D-3759 / AFERA 4005	8 %
Adhesion to Stainless Steel e.g. 90°/180° peel @room temp, 72 hr dwell, jaw speed 300mm/min AFERA 4001	9.5 N/25 mm								
Temperature Performance	90 °C								
Tensile Strength e.g. ASTM D-3759 / AFERA 4004	122 N/25 mm								
Elongation at Break ASTM D-3759 / AFERA 4005	8 %								

Satisfactory performance and clean removal of Scotch® Tape 202 will be achieved at varying temperatures/time exposure on many substrates. Tests should be conducted to establish Scotch® Tape 202 performance parameters in your process conditions. The optimum level for product performance and easy removal is at 90 °C for 60 min.

Application Performance	Scotch® Tape 202 can be used for many general purpose masking applications. It excels at paint masking and can be used for bundling, protecting or any other similar job. This general use tape is able to withstand a temperature of 90 °C for one hour.
Storage	Store 3M 2526 in a clean dry place. Temperature of 21 °C and 50 percent relative humidity are recommended
Shelf Life	3M has a shelf life of e.g. 12 months from date of dispatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity
For Additional Information	To request additional product information or to arrange for sales assistance, call: 08-92 22 50 Address correspondence to: 3M Svenska AB, Industri, 191 89 Sollentuna
Important Notice	All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark of the 3M Company.



**3M Svenska AB
Industri**

Bollstanäsvägen 3
191 89 Sollentuna

Tel: 08-92 22 50

Fax: 08-92 22 88

E-post: kundservice@mmm.com

www.3M.se/tejp