

CCMT 3(2.5)1 NN LT 10 & LT 1000

Speeds & Feeds

Material Group	Gr. N°	VDI Group	Material Examples*	Hardness	D.O.C. [inch]		Feed [inch/rev]		Amax	V _c [sfm]		Suggested Starting Parameters				
					min	max	min	max		min	max	D.O.C.	Feed	V _c		
Steel	Non-alloyed	1	C35, Ck45, 1020,	125 HB	0.008	0.118	0.004	0.009	0.0009	590	1080	0.079	0.007	980		
		2	1045, 1060,	190 HB		0.098		0.009	0.0008		910			850		
		3	28Mn6	250 HB		0.098		0.008	0.0007		820			780		
	Low alloyed	2	6	42CrMo4, St50, Ck60, 4140, 4340, 100Cr6	180 HB	0.008	0.098	0.004	0.008	0.0008	390	910	0.079	0.006	850	
			4,6		230 HB		0.098		0.008	0.0007		820			780	
			5,7		280 HB		0.079		0.007	0.0006		680			650	
			8		350 HB		0.079		0.007	0.0006		590			590	
	High alloyed	3	10	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.008	0.098	0.004	0.007	0.0006	220	620	0.079	0.005	590	
			10		280 HB		0.098		0.006	0.0006		490			450	
			11		320 HB		0.079		0.006	0.0005		420			390	
			11		350 HB		0.079		0.006	0.0004		360			360	
	Stainless Steel	Austenitic	4	304, 316, X5CrNi18-9	180 HB	0.008	0.098	0.004	0.007	0.0005	550	880	0.079	0.005	850	
14			240 HB		0.098		0.007		0.0004	520		720			680	
Duplex		5	X2CrNiN23-4, S31500	290 HB	0.008	0.079	0.004	0.006	0.0003	260	490	0.079	0.005	450		
		14		310 HB		0.079		0.006			220			450	450	
Ferritic & Martensitic		6	410, X6Cr17, 17-4 PH, 430	200 HB	0.008	0.098	0.004	0.007	0.0005	550	820	0.079	0.006	780		
		13		42 HRC		0.079		0.006	0.0004		390			620	590	
Cast Iron	Grey	7	GG20, GG40, EN-GJL-250, No30B	150 HB	0.008	0.118	0.003	0.008	0.0010	550	820	0.079	0.007	780		
		15		200 HB		0.118		0.008	0.0009		520			750	720	
		16		250 HB		0.118		0.008	0.0009		490			680	650	
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.008	0.098	0.003	0.007	0.0007	390	820	0.079	0.006	780		
		17,19		200 HB		0.098		0.007	0.0006		750			720		
		18,20		250 HB		0.098		0.007	0.0006		620			590		
High Temp. Alloys	Fe, Ni & Co based	9	Incoloy 800	240 HB	0.008	0.079	0.004	0.006	0.0004	80	160	0.079	0.005	130		
		33		Inconel 700		250 HB		0.079			0.006			80	160	130
		34		Stellite 21		350 HB		0.079			0.006			70	140	110
	Ti based	10	TiAl6V4 T40	-	0.008	0.079	0.004	0.006	0.0005	140	210	0.079	0.006	190		
		37		-		0.079		0.006	0.0004		110			190	160	
	Hardened Mat.	Steel	11	X100CrMo13, 440C, G-X260NiCr42	45 HRC	0.008	0.071	0.002	0.005	0.0003	160	320	0.059	0.004	290	
38			50 HRC		0.059		0.004		0.0003	130		290			260	
38			55 HRC		0.055		0.004		0.0002	130		260			220	
Chilled Cast Iron		40	Ni-Hard 2	400 HB	0.008	0.063	0.002	0.005	0.0003	130	190	0.047	0.004	160		
White Cast Iron		41	G-X300CrMo15	55 HRC	0.008	0.055	0.002	0.004	0.0002	90	160	0.039	0.003	130		
NF	Al (>8%Si)	12	25	AlSi12	130 HB	0.008	0.157	0.004	0.012	0.0011	650	1310	0.079	0.008	1140	



(800) 597-3921 or (317) 803-8000 for Application Support.
For additional suggested Speeds & Feeds: <http://delivr.com/1kppm>

