



Natural
Rubber Latex



Lab & Utility

TouchNTuff®

ADVANCED PRODUCT & WORKER PROTECTION

69-210 69-318 Natural Rubber Latex Glove

Handle the most intricate and delicate products with incredible sensitivity

FEATURES AND BENEFITS:

Comfort, Strength and Sensitivity

The strength and comfort of 100% natural rubber latex, 5 mil thickness for the highest degree of sensitivity

2 versions available to better fit your needs

69-210: Powdered, Smooth Grip

69-318: Powder Free, Textured Finish for better grip

Food Compliant

Both the TouchNTuff® 69-210 and 69-318 comply with FDA food handling requirements (21 CFR 177.2600).



WARNING: This product contains natural rubber latex which may cause allergic reactions in some individuals.

*Style 69-318 formerly known as Conform®XT

*Style 69-210 formerly know as Conform®

TECHNICAL DATA SHEET:

PRODUCT INFORMATION:

	69-210	69-318
Material	Natural Rubber Latex	
Color	Natural	
Glove Design	Ambidextrous, Powdered, Smooth Grip	Ambidextrous, Powder Free, Textured Grip
Cuff	Beaded Cuff	
Audit Standards	ISO 9001:2008, ISO 13485:2003, US FDA 21 CFR PART 820 (QSR), and Canadian MDR	
Quality Control	Incoming for both raw materials and packaging materials, in-process (QA pre-packing inspection) and final release (QA pre-shipment inspection) for all gloves produced.	
Packaging	100 gloves per dispensers, 10 dispensers per shipper carton, 1000 gloves per shipper carton	
Storage	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.	
Country of Origin	Malaysia	

PHYSICAL PROPERTIES:

PROPERTY		TYPICAL VALUES					TESTING METHOD
		XS 5½ - 6	S 6½ - 7	M 7½ - 8	L 8½ - 9	XL 9½ - 10	
SIZE							ASTM D3767/EN 420
Length (mm)	69-210	NA	240	240	240	240	
	69-318	240	240	240	240	240	
Average Palm Width (mm)	69-210	NA	80	95	102	111	
	69-318	75	85	95	106	116	

Freedom from Holes (Inspection level I)	1.5 AQL	ASTM D5151/EN 374-2
---	---------	---------------------

Palm Thickness Single Wall	(mm:0.12) / (mils:5)	ASTM D3767/EN 420
----------------------------	----------------------	-------------------

	BEFORE AGING	AFTER AGING	
Ultimate Tensile Strength	Min 18 Mpa	Min 14 Mpa	ASTM D 412-06a
Elongation at Break (%)	Min 650	Min 500	ASTM D 412-06a

ORDERING INFORMATION:

	SIZE	XS	S	M	L	XL
69-210	ASPN	NA	516704	516705	516706	516707
	ORACLE	NA	104986	104987	104988	104989
69-318	ASPN	516699	516700	516701	516702	516703
	ORACLE	104985	105072	105073	105074	105075



CE 0493

For additional information visit us at www.ansell.com, or call us at

North America: +1800 800 0444

Latin America: +55 11 3356 3100

Asia Pacific: +852 2185 0600

Europe: +32 2 528 74 00

Australia: +61 1 800 337 041

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2014 All Rights Reserved.

06262014