

September, 2002

## 3M™ Adhesive Transfer Tape F9755PC

### Product Description

3M™ Adhesive Transfer Tape F-9755PC with 3M™ Adhesive 420 is a high performance adhesive system that offers the ability to make adhesive bonds at temperatures as low as 32°F (0°C). This product utilizes a 58 lb. polycoated liner for moisture stability.

### Product Features

Adhesive 420 is a medium firm acrylic pressure-sensitive adhesive system. It features high adhesion to a variety of surfaces, excellent shear holding power, high temperature resistance and excellent UV resistance.



**Technical Information Note**

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

**Typical Physical Properties**

Property	Values	
Color	Clear	
Total Tape Thickness without liner	0.13 mm	5 mil
Adhesive Type	420	
Adhesive Carrier	None	
Liner	Moisture Resistant Paper	
Liner Thickness	0.1 mm	4 mil
Liner Color	Tan	

**Typical Performance Characteristics**

Property	Values		Method	Substrate
Peel Adhesion	6 N/cm	55 oz/in	ASTM D3330	Stainless Steel
Solvent Resistance	Very Good			
UV Resistance	Excellent			

Relative High Temperature Operating Ranges		Test Condition
232 °C	450 °F	Short Term (minutes, hours)
149 °C	300 °F	Long Term (days, weeks)

Property: Relative High Temperature Operating Ranges

Static Shear	Test Condition
>10,000 min	1000 g @ Room Temperature
>10,000 min	500 g @ 70°C (158°F)
>10,000 min	400 g @ 93°C (200°F)
>10,000 min	300 g @ 121°C (250°F)
>10,000 min	300 g @ 149°C (300°F)
>10,000 min	300 g @ 177°C (350°F)

Table continued on next page

**Typical Performance Characteristics (continued)**

Static Shear	Test Condition
>10,000 min	200 g @ 232°C (450°F)

Property: Static Shear  
 Method: ASTM D3654  
 Dwell/Cure Time: 72 hr  
 Substrate: Stainless Steel  
 Backing: Aluminum Foil  
 notes: 1 x 1 in Area Contact

180° Peel Adhesion		Substrate
7.5 N/cm	70 oz/in	Stainless Steel
6.8 N/cm	63 oz/in	Painted Metal
7.5 N/cm	70 oz/in	Glass
6.5 N/cm	74 oz/in	Polycarbonate (PC)
6.5 N/cm	74 oz/in	Acrylic (PMMA)
8.3 N/cm	77 oz/in	Epoxy
8.6 N/cm	80 oz/in	ABS
4.3 N/cm	40 oz/in	Polypropylene (PP)
1.6 N/cm	15 oz/in	Low Density Polyethylene (LDPE)
2.7 N/cm	25 oz/in	High Density Polyethylene (HDPE)

Property: 180° Peel Adhesion  
 Method: ASTM D3330  
 Test Condition : Room Temperature

**Available Sizes**

Property	Values	
Note	Subject to Minimum Order Requirements	
Standard Length	54.9 m	60 yd
Minimum Available Width	1/2 in	
Maximum Available Width	54 in	
Normal Slitting Tolerance	±0.8 mm	±1/32 in
Core Size (ID)	76.2 mm	3 in

Maximum Length		Width
165 m	180 yd	1/2 in to 1 in widths
329 m	360 yd	1 in to maximum

Property: Maximum Length

## Handling/Application Information

### Application Ideas

- These tapes are ideal for joining a variety of similar and dissimilar materials where high bond strength and high temperature performance are required and are also ideal for many applications where excellent UV resistance is required.
- 2 mil thick tapes can generally be used for joining materials that are relatively smooth, thin and have low residual stress. For materials with a rough or textured surface, the thicker adhesive film of the 5 mil tapes would be more appropriate for evaluation.

### Application Techniques

- Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improve bond strength.
- To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol and water (rubbing alcohol) or heptane. Note: Be sure to follow the manufacturer’s precautions and directions for use when using solvents.
- Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended for most pressure sensitive adhesives because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory. 3M™ Adhesive Transfer Tapes F-9752PC and F-9755PC can be bonded at temperatures as low as 32°F (0°C).
- Ultimate bond strength can be accelerated by exposure of the bond to elevated temperatures, such as 150°F (66°C) for about one hour.

### Application Equipment

For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

### Storage and Shelf Life

Product retains its performance and properties for 24 months from date of manufacture when stored in original cartons at 70°F (21°C) and 50% relative humidity.

## References

### Safety Data Sheet (SDS)

[https://www.3m.com/3M/en\\_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en\\_US&co=ptn&q=F9755PC](https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=F9755PC)

## Family Group

	F9752PC	F9755PC
Relative High Temperature Operating Ranges (°C) Test Condition: Short Term (minutes, hours)	232	232
Relative High Temperature Operating Ranges (°C) Test Condition: Long Term (days, weeks)	149	149
Color	Clear	Clear
Total Tape Thickness without liner (mm)	0.05	0.13
Adhesive Type	420	420

Table continued on next page

**Family Group (continued)**

	F9752PC	F9755PC
Adhesive Carrier	None	None
Liner	Moisture Resistant Paper	Moisture Resistant Paper
Liner Thickness (mm)	0.1	0.1
Liner Color	Tan	Tan

**ISO Statement**

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

**Important Notice**

3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user’s method of application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user’s knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user’s method of application.

**For Additional Information**

To request additional product information or to arrange for sales assistance, call toll free 1-800-362-3550 or visit [www.3M.com/adhesives](http://www.3M.com/adhesives). Address correspondence to: 3M Engineered Adhesives Division, 3M Center, Building 220-7E-01, St. Paul, MN 55144-1000. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

**Recognition/Certification**

MSDS 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration’s Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, the products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards. TSCA These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.

**Limitation of Remedies and Liability**

If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M’S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.

